



SOYA WAX SP55-40

Technical Characteristics

Test	Method	Unity	Value
Color	VISUAL	-----	White / Ivory
Congeaing point	ASTM D 938	°C	32 - 42
Drop Melting point	ASTM D 127	°C	48 - 52
Kinematic Viscosity at 100 °C	ASTM D 445	cSt	7 - 12
Penetration at 25°C	ASTM D 1321	1/10 mm	45 - 65

PROREUSE SRLS

Via Torino ,30

10070 Vallo (TO)

www.proreuse.it – www.eshop-candelx.it

P.IVA 11363280014

n° REA TO 1207464 Cap. Soc. : 2.000,00 euro

Tel.+39 011 92 49436 - E-mail: proreuse1622@gmail.com